

Nástrojové oceli na výrobu forem

W.Nr.	ČSN	DIN	AISI	●	■
1.2083	~	X42Cr13	420	x	x
1.2085	~	X33CrS16	420+S	x	x
1.2162	19487	21MnCr5	~		x
1.2311	19520	40CrMnMo7	P20	x	x
1.2312	19520+S	40CrMnMoS8-6	P20+S	x	x
1.2316	~	X38CrMo16	420	x	x
1.2738	~	40CrMnNiMo8-6-4	P20+Ni		x
1.2738 HH QT 32-36 Hrc					x
1.2738 HH QT Supreme 38-42 Hrc					x
1.2764	~	X19NiCrMo4	~	x	x