

Otěrovzdorné oceli

W.Nr.	ČSN	DIN	AISI	●	■
1.0503	12050	C45	1043	x	x
1.057	11523	S355J2G3 (St 52-3) (Fe510D1)		x	x
1.0601	12061	C60	1050		x
1.1191	12050	C45E / Ck 45	1042	x	x
1.3505	14109	100Cr6	52100	x	
1.4034	17024	X46Cr13	420	x	
1.4057	17145	X17CrNi16-2		x	
1.6582	16343	34CrNiMo6	4340	x	
1.6587	16326	17CrNiMo6 (18CrNiMo7-6)		x	
1.658	823M30	30CrNiMo8		x	
1.7035	~	41Cr4	5135H	x	
1.7131	14220	16MnCr5	5115	x	x
1.7147	14221	20MnCr5	5120H	x	x
1.7225	15142	42CrMo4	4140	x	x
1.8159	15260	51CrV4	6150		x
S690QL	vysokopevnostní				x
28MnB5					x
Hardfield 400					x
Hardfield 500					x